



Product Information Flyer

DESCRIPTION

CIMSTAR 60 is a semi-synthetic metalworking fluid.

APPLICATION

CIMSTAR 60 was developed for use on ferrous and most non-ferrous materials. It can be used on mild steels, stainless steels, hardened steels, most aluminum alloys and exotic materials. It should not be used on magnesium alloys.

For use in moderate to heavy duty machining and grinding applications, such as milling, drilling, cut tapping, reaming, boring and CBN, ID and centerless grinding.

FEATURES & BENEFITS

VERSATILE PRODUCT:

Good lubricity – physical, chemical, and extreme pressure lubricant agents provide good machining and grinding ability.

CORROSION PROTECTION:

The oily residue keeps machine tools and work-piece materials free of corrosion and staining. Good on most non-ferrous alloys as well.

MICROBIAL CONTROL:

CIMSTAR 60 has good rancidity control if product concentration is properly controlled.

FOAM CONTROL:

CIMSTAR 60 has good foam control.

RECOMMENDED STARTING DILUTIONS

CIMSTAR 60 is to be mixed with water for use. Always add concentrate to water. Fluid may be more difficult to mix when water temperature is below 55 F (13 C). Add no other materials to the concentrate or mix unless approved by your CIMCOOL® District Manager.

Grinding	5% - 10%	(1:20 to 1:10)
Machining	5% - 10%	(1:20 to 1:10)

CONCENTRATION

An MI Titration, Non-solvent Titration, Total Alkalinity, CIMCHEK™ Test Strip or Refractometer can be used.

The Refractometer Factor is 1.8

Multiply the scale reading obtained on your CIMCOOL® Refractometer by this factor to obtain the mix concentration in percent. Calibrate the refractometer so that it reads 0.0 with water before testing the sample mix. Remove gross contaminants from the sample mixes before testing. A refractometer is only recommended for use in checking the concentration of a fresh charge.

TYPICAL PHYSICAL AND CHEMICAL PROPERTIES

Physical State: Liquid

Solubility in water: 100% miscible

Viscosity (SUS) @ 100°F: 200

pH Concentrate: 9.8

Total Chlorine/Chloride, wt%: 3.6/<50ppm

Silicones: YES

Appearance and Odor: Hazy/Chemical

Weight, lb/gal, 60°F (15.6 °C): 8.5

Flash Point /Sp.Gr./Boiling Point: SEE MSDS

pH Mix 5%, Typical Operating: 8.8

Total Sulfur, wt%: 0.3

HANDLING and STORAGE

If frozen, product separates. Thaw completely at room temperature and stir thoroughly before use. Inside storage is recommended.

SAFETY DATA SHEET

Available at www.cimcool.com

For additional information refer to its OSHA MSDS, website or contact your local CIMCOOL TECHNICAL SPECIALIST OR DISTRICT MANAGER, or you may contact CIMCOOL® Technical Services at 1-513-458-8199.

Limitation of Liability: Under no circumstances, shall we or any affiliate of ours have any liability whatsoever for loss of use, or for any indirect or consequential damages. Minor formulation changes or normal variations in the manufacture of this product may cause slight variances in the data presented on this sheet.