

CIMCOOL®

METALWORKING FLUIDS

CIMSTAR® 40LF

SEMISYNTHETIC, METALWORKING FLUID CONCENTRATE

APPLICATIONS	<p>CIMSTAR® 40LF is designed to be used in machines and operations where long fluid life is needed, such as in large individual machine or central system reservoirs. It is recommended for moderate-duty machining and grinding of ferrous metals, and some nonferrous metals.</p> <p>Metals: Cast Iron, Nodular Iron, Carbon Steels, High Speed Steel, High Alloy Steels, Stainless Steels, Aluminum</p> <p>Duty Range: For light to moderate-duty operations</p>
FEATURES & BENEFITS	<p>CIMSTAR® 40LF is a clear, water soluble, semisynthetic product, designed to be low foaming in soft water (50-ppm hardness).</p> <p>ADVANTAGES - Exceptional rancidity control - Effective lubrication and cooling - Good settling properties</p> <p>EFFECTIVE LUBRICATION AND COOLING - A combination of chemical lubricants and wetting agents provide good machining and grinding properties - Keeps parts and tools cool - Extends tool life - Allows high speeds and feeds that increase production</p> <p>STABLE - Can be used in individual machines as well as central system applications</p> <p>GOOD SETTLING PROPERTIES - Efficiently settles chips and grit - Produces a good cake on positive filters which removes recirculating fines and also lowers media usage - Parts and machines stay clean</p> <p>EXCELLENT CORROSION CONTROL - Organic and inorganic corrosion inhibitors protect machines and parts from rust</p> <p>ENVIRONMENTALLY FRIENDLY - Is easy to maintain and control - It is waste treatable - It can also be recycled for reuse</p>

<p>RECOMMENDED STARTING DILUTIONS</p>	<p>FOR INDUSTRIAL USE ONLY Recommended Starting Dilution: 5% (1:20) Typical Operating Range: 5% (1:20) to 10% (1:10) For concentrations outside this range contact CIMCOOL® Technical Service at 513-458-8199.</p> <p>CIMSTAR® 40LF is to be mixed with water for use (add concentrate to water). Add no other substances to the concentrate or mix unless approved by CIMCOOL® Technical Services.</p> <p>Not recommended for use with magnesium or alloyed magnesium.</p> <p>For concentration analysis, use the MI Titration Procedure, Non-Solvent Titration Procedure, Total Alkalinity Titration Procedure, CIMCHEK™ Test Strip, or Refractometer.</p>
<p>TYPICAL PHYSICAL AND CHEMICAL PROPERTIES</p>	<p>Physical state: Liquid Appearance and odor: Clear / Chemical Colors available: Pink Solubility in water: 100% Miscible Weight, lb/gal, 60°F (15.6°C): 8.85 Specific gravity, (H₂O = 1): 1.06 Boiling point, °F (°C): 212 (100) Flash point, COC, °F (°C): None, Self Extinguishing Fire point, COC, °F (°C): NA Freezing point (or pour point), °F, (°C): 32 (0) Protect from Freezing. pH, concentrate: 10.2 pH, 5.0% mix, typical operating conditions: 8.9 Total chlorine/chloride, wt%, calculated: 0.00/< 50 ppm Total sulfur, wt%, calculated: 0.01 Silicones: Yes</p>
<p>PACKAGING</p>	<p>Available in 5-gallon pails, 55-gallon drums, and bulk containers.</p>
<p>REFRACTOMETER FACTOR = 2.9 Multiply the scale reading obtained on your CIMCOOL® Metalworking Fluid or other acceptable refractometer by the Refractometer Factor to obtain the mix concentration in percent.</p> <p>NOTE: Calibrate the refractometer so that it reads 0.0 with water, before testing the sample mix. Remove gross contaminants from the sample mix before testing.</p>	
<p>For additional information concerning CIMSTAR® 40LF, refer to its OSHA MSDS or contact CIMCOOL® Technical Services at 1-513-458-8199. Reprints/Updates of this Product Information Flyer (PIF) can be found on our web site, WWW.CIMCOOL.COM or from your Milacron representative.</p> <p>Minor formulation changes or normal variations in the manufacture of this product may cause slight variances in the data presented on this sheet. Consumable Products Division/ Milacron Marketing Company Cincinnati, Ohio 45209</p> <p>PC-9978 6/8/05</p>	

