

# MILFORM<sup>®</sup>

## METALFORMING FLUIDS

### MILFORM<sup>®</sup> 8060

#### APPLICATIONS

MILFORM<sup>®</sup> 8060 is a synthetic fluid for severe-duty stamping, piercing, punching, and drawing of ferrous and some non-ferrous metals.

#### FEATURES & BENEFITS

- EXCELLENT LUBRICITY
- GOOD CORROSION CONTROL
- SIGNIFICANTLY IMPROVES TOOL AND DIE LIFE
- FORMULATED TO REPLACE CHLORINATED STRAIGHT OILS
- GOOD WELD THROUGH PROPERTIES
- GOOD CLEANLINESS CHARACTERISTICS

**RECOMMENDED  
STARTING  
DILUTIONS****FOR INDUSTRIAL USE ONLY.**

Use between 8% (1:12.5) and 40% (1:2.5) for moderate to heavy-duty stamping and drawing of ferrous and some non-ferrous metals.

**MILFORM<sup>®</sup> 8060** is to be mixed with water for use (add concentrate to water).

Add no other substances to the concentrate or mix unless approved by Technical Services (1-513-458-8199).

Not recommended for use with magnesium or alloyed magnesium.

For concentration analysis, use the MI Titration Procedure, Non Solvent Titration Procedure, or Refractometer.

**TYPICAL  
PHYSICAL  
AND  
CHEMICAL  
PROPERTIES**

**Physical state:** Liquid

**Appearance and odor:** Clear / Chemical

**Solubility in water:** Complete

**Weight, lb/gal, 60°F (15.6°C):** 8.6

**Specific gravity, (H 20 =1):** 1.03

**Boiling point, °F (°C):** 212 (100)

**Flash point, COC, °F (°C):** None, Self Extinguishing

**Fire point, COC, °F (°C):** None, Self Extinguishing

**Freezing point (or pour point), °F (°C):** 32 (0)

If frozen, thaw completely at room temperature.

**pH, concentrate:** 8.5

**pH, 25.0% mix, typical operating conditions:** 8.3

**Total chlorine/chloride, wt%, calculated:** 0.00/<50 ppm

**Total sulfur, wt%, calculated:** 1.40

**Total phosphorus, wt%, calculated:** 0.06

**Silicone:** Yes

**PACKAGING**

Available in 5-gallon pails, 55-gallon drums, and bulk containers.

**REFRACTOMETER FACTOR = 2.0** Multiply the scale reading obtained on your CIMCOOL<sup>®</sup> Metalworking Fluid or other acceptable refractometer by the **Refractometer Factor** to obtain the mix concentration in percent.

**NOTE: Calibrate the refractometer so that it reads 0.0 with water, before testing the sample mix. Remove gross contaminants from the sample mix before testing.**

**WARRANTY:** Milacron Products Division will grant credit on any product which proves defective in material or workmanship as determined by us subject to the following conditions: all material is subject to our inspection prior to issuing credit; any refund will be adjusted based on the volume of product used; no credit will be granted for used or unused product(s) over one year old as determined by the batch number. The terms in this warranty do not in any way extend to any product thereof covered by this agreement, which has a life, under normal usage, inherently shorter than the one-year period indicated above. Except as set forth expressly in writing herein, there are no other warranties express or implied in respect of any product. No warranty of merchantability or fitness for purpose shall apply.

**LIMITATION OF LIABILITY:** Under no circumstances shall we or any affiliate of ours have any liability whatsoever for loss of use or for any indirect or consequential damages.

Minor formulation changes or normal variations in the manufacture of this product may cause slight variances in the data presented on this sheet.

Global Industrial Fluids / Milacron Marketing Company  
Cincinnati, Ohio 45209